



台灣檢驗科技股份有限公司
SGS Taiwan Ltd.

248台北縣五股工業區五工路136 1號
136-1 Wu Kung Road, Wuku Industrial
Zone, Taipei County, Taiwan 248
Tel :2299-3939
Fax:(886-2)2299-3227

248台北縣五股工業區五權路35號
35, Wu Chyuan Road, Wuku Industrial
Zone Taipei County, Taiwan 248
Tel :2298-3355 Ext.700
Fax:(886-2)2299-7857

434台中縣龍井鄉遊園北路115號
No. 115, Youyuan N, Rd., Lungjing
Shiang, Taichung County, Taiwan 434
Tel :(886-4)2631-1838
Fax:(886-4)2631-1190

807高雄市三民區中華二路266號
266, Chung Hwa 2nd Road San Min
District Kaohsiung, Taiwan 807
Tel :(886-7)323-0920
Fax:(886-7)315-7484

Test Report

No: TXD1670 I2002 IHC

Date: DEC. 30, 2002

Page: 1 OF 2

TAIWAN TEXTILE FEDERATION
13F, TTF BUILDING, 22 AIKUO EAST ROAD,
TAIPEI 100, TAIWAN, R.O.C.

The following sample was submitted and identified by the client as:

SAMPLE DESCRIPTION: ONE KNITTED FABRIC WITHOUT NANO RED FIBERS IN GRAY PINK
(BLANK SAMPLE)
ONE KNITTED FABRIC WITH NANO RED FIBERS IN GRAY PINK
(TESTING SAMPLE)

STYLE/ITEM NO.: K15N6 150/144 TAYF-GN-FI

MANUFACTURER/VENDOR: LEALEA ENTERPRISE CO., LTD.

SAMPLE RECEIVING DATE: DEC. 25, 2002

TEST STARTING DATE: DEC. 25, 2002


Test Item:
The absorption for far infrared

Test Method:
According to the far-infrared textile test method of Taiwan Textile Federation(TTF-0002).

	<u>1st test</u>	<u>2nd test</u>	<u>3rd test</u>	<u>mid. results</u>
Test Results:				
Peak- area of blank sample	36.647	36.533	36.578	36.578
Peak- area of testing sample	45.919	45.490	46.002	45.919
Different Peak- area rate for testing and blank sample	20.3%			

Conclusion:
The different absorption for far infrared of sample conform to Taiwan Textile Federation's specification.

Signed for and on behalf of
SGS Taiwan Ltd.


Cheng Mei Wan
Asst. Manager

This results shown in the test report refer only to the sample(s) tested unless otherwise stated.
The test report cannot be reproduced except in full, without prior written permission of the Company.

