

TEST REPORT

NUMBER: TXT715963

APPLICANT: LI PENG ENTERPRISE CO., LTD.

DATE: JUL 07, 2004

6/F., NO. 162,
SUNG CHIANG RD.,
TAIPEI, TAIWAN,
R. O. C.

SAMPLE DESCRIPTION:

ONE (1) PJECE OF SUBMITTED SAMPLE SAID TO BE NYLON INTERLOCK
IN GREY.


ORDER NO. : A08491 (60" X 190 G/Y)

TESTS CONDUCTED:

AS REQUESTED BY THE APPLICANT, FOR DETAILS REFER TO ATTACHED PAGE(S)

PREPARED AND CHECKED BY :
FOR INTERTEK TESTING SERVICES
TAIWAN LTD.

AUTHORIZED BY :
FOR INTERTEK TESTING SERVICES
TAIWAN LTD.


CAROL PENG
MANAGER
TEXTILE & FOOTWEAR DIVISION


Lori Kuo

LORI KUO
GENERAL MANAGER
TEXTILE & FOOTWEAR DIVISION

LISA / rchen

PAGE 1 OF 2

Intertek Testing Services Taiwan Ltd.

14F, 27, Chung Shan North Road, Sec. 3, Taipei, Taiwan, R.O.C.

全國公證檢驗股份有限公司

台北市中山北路三段27號14樓

Tel: (+886-2) 2592-6033 · 2597-9955 Fax: (+886-2) 2591-8328 · 2595-9410

TEST REPORT

NUMBER: TXT715963

TESTS CONDUCTED (AS REQUESTED BY THE APPLICANT)

DETERMINATION OF THE UVR TRANSMISSION OF DRY TEXTILE
(AS/NZS4399:1996, APPENDIX A)

WAVELENGTH RESOLUTION : 2 NM

SOLAR SPECTRUM IRRADIANCE USED; NOON ON 17 JANUARY 1990 FOR
MELBOURNE (38°S)

NO. OF SCANS : 8

THE SAMPLES ARE TESTED IN DRY AND RELAXATION STATE

MEAN UPF 47

UPF RATING 50

UVR PROTECTION CATEGOR EXCELLENT PROTECTION

% OF MEAN UVA 5.07%

TRANSMITTANCE
(315-400 NM.)

% OF MEAN UVB 1.6%

TRANSMITTANCE
(290-315 NM.)

NOTE : UPF RANGE	PROTECTION CATEGORY
15 TO 24	GOOD PROTECTION
25 TO 39	VERY GOOD PROTECTION
40 TO 50, 50+	EXCELLENT PROTECTION

***** E N D *****